



HORSE SADDLE OIL

Thickness	1,6-1,8
Leather Types	Full Grain - Semi Aniline - Through dyeing aniline
Raw Material	Bovine Raw hide
Tannage	Chromium salt

COLOR FASTNESS

Property	Test Method	Performance
Dry rub fastness, 100 cycles - Discharge	EN ISO 11640	≥ 4 Grey Scale
Dry rub fastness, 100 cycles - Degradation	EN ISO 11640	≥ 4 Grey Scale
Wet rub fastness, 20 cycles - Discharge	EN ISO 11640	≥ 3 Grey Scale
Wet rub fastness, 20 cycles - Degradation	EN ISO 11640	≥ 3 Grey Scale
Sweat rub fastness, 20 cycles - Discharge	EN ISO 11640 / EN ISO 11641	≥ 3 Grey Scale
Sweat rub fastness, 20 cycles - Degradation	EN ISO 11640 / EN ISO 11641	≥ 3 Grey Scale

PHYSICAL CHARACTERISTICS

Property	Test Method	Performance
Tear strenght	EN ISO 3377-1	≥ 20 N

The article is manufactured in compliance with the REACH directive and complies with the latest version of the RSL_Dani